**Pavement Testing Services Ltd**
**Unit 7**
**Cowling Business Park**
**Canal Side**
**Chorley**
**PR6 0QL**

T: 01257 233 242
F: 01257 234 744
E: info@ptsinternational.co.uk

**4076**

# Laboratory Test Report

**Determination of Resistance to Fragmentation (Los Angeles coefficient) EN 1097-2:1998**

| | |
|---|---|
| **Client :** | Gallaghers |
| **Client Address :** | James Corbett Road<br>Salford<br>Manchester |
| **Contract :** | Gallaghers Routine testing |
| **Job No. :** | PTS1119-G-01-A |
| **Report No.:** | PTS1119-G-01-A-99 |

## Sample Details

| | |
|---|---|
| **Material Description :** | Recycled Material as Type 1 Subbase |
| **Laboratory Number :** | Lab/11/4937 |
| **Client Ref. :** | Gal29/11/2011 |
| **Source :** | Site Produced |
| **Sample Location :** | Stockpile |
| **Date Sampled :** | 29/11/11 |
| **Sampled By :** | JH |
| **Date Received :** | 29/11/11 |
| **Date of Test :** | 05/12/11 |

## Test Results

| | |
|---|---|
| **Test portion size fractions :** | Passing 14mm Retained 12.5mm<br>Passing 12.5mm Retained 10mm |

**Los Angeles Coefficient (LA)** **29**

## Deviations from Test Method

None

**Comments** Sample complies with SHW Cl 803 (Subbase)

**Signed** _____ **J.Hopkinson(Senior Technician)**

**Report Date :** 15/12/11