



4076

**SIEVE ANALYSIS**


Report No. 1119-G-01-A-100

Client: Gallaghers  
 Site: James Corbett Road, Salford  
 Location: Site Laboratory Ref: Lab/11/4937  
 Date Sampled: 29/11/11 Client Ref. Gal29/11/2011  
 Sampled from: Stockpile Mass (kg): 160  
 Supplier: Client Source: Site  
 Description: Type 1 Subbase + SMR

Material Specification: SHW Table 8/5 (Overall Range)  
 Sampled by: Client  
 Date received: 29/11/11  
 Sample type: Bulk  
 Method of Preparation:

Remarks: Sample complies with grading specification

BS Sieve (mm)	Passing (%)	Material Specification		
90				
80				
75				
63	100	100		
40	100			
31.5	89	75	-	99
20	80			
16	75	43	-	81
14	70			
10	60			
8.0	54	23	-	66
6.3	49			
4.0	42	12	-	53
2.0	35	6	-	42
1.0	29	3	-	32
0.500	24			
0.250	17			
0.125	11			
0.063	8.0	0	-	9



Certified that the Particle Size Distribution was determined in accordance with EN 933-1

Signed \_\_\_\_\_ ( ) M. Hayes (Laboratory Manager)  
 ( ) D.Foster(Assistant Laboratory Manager)  
 (X) J.Hopkinson(Senior Technician)